

GOMTEX®USA

CONSTRUCTION

Interior and exterior layer:

Specially-formulated nitrile rubber, extruded through the circular fabric. Minimal flow loss thanks to its smooth interior wall. High thermal resistance.

Reinforced grooves for better abrasion making it easy to use. **Reinforced middle textile:**

Circular weaved outer layer made from high tenacity polyester thread with breakage > 62 bars (900 psi). No defects (broken threads, knots, etc.)

PERFORMANCE

- Excellent resistance to abrasion and intensive use by professionals thanks to its reinforced grooves.
- Highly resistant to oil, gasoline and a wide range of chemicals.
- Very resistant to both contact and radiant heat.
- Flexible hose even at low temperatures (-15°C).
- High breaking strength> 62 bars (900 psi) thanks to its
 specially-made textile.
- No maintenance or drying necessary.

APPLICATIONS

- · Fire-fighting and industrial use.
- Refineries.
- Military use.
- Airports.
- · Forestry.

TECHNICAL CHARACTERISTICS

DIAMETER		WEIGHT	THICKNESS	WORKING PRESSURE	TEST PRESSURE	BURST PRESSURE
inches	mm.	gr/m.	mm.	Bars	Bars	Bars
1"	25	305	2,70	30	60	>90
1 ½"	38	480	3,10	20	40	>62
1 ³ / ₄ "	45	500	3,00	20	40	>62
2"	52	590	3,30	20	40	>62
2 ½"	64	750	3,30	20	40	>62
23/4"	70	825	3,50	20	40	>62
3"	75,5	860	3,50	20	40	>62